

# SAAFCarb™ MA Plus

## ENGINEERED GAS REMOVAL CHEMICAL MEDIA

### Features and Benefits

- Non-flammable
- Non-toxic
- Designed for acid gases
- Easy disposal, fully incinerable
- Does not support desorption

### Engineered Media

SAAFCarb MA Plus engineered gas removal chemical media is designed to efficiently remove up to 99,5% of specific acid gaseous contaminants from airstreams. Target contaminants include:

- Hydrogen Sulfide (H<sub>2</sub>S)
- Sulfur dioxide (SO<sub>2</sub>)
- Chlorine (Cl<sub>2</sub>)
- Hydrocarbons (VOC's)

Manufactured of pelletized activated carbon, SAAFCarb MA Plus engineered media is composed of high quality substrates with catalytic and / or chemical impregnation in order to provide optimum chemisorption and catalytic reaction for various sour gases. Impregnations are applied uniformly during pellet formation and are distributed throughout the pellet volume. This process provides the maximum amount of impregnate for chemical reaction and optimal performance.

### Chemisorptive Process

SAAFCarb MA Plus impregnated media removes acid contaminants in their reversible chemisorptive process by chemical and / or catalytic reaction. In this process, the gas is trapped within the pellet and chemical or catalytic reaction changes the gases into harmless solids, thereby eliminating the possibility of desorption. SAAFCarb™MA media allows this to be an instantaneous, irreversible, and safe chemical reaction.


### Quality Control

SAAFCarb MA Plus media undergoes the following quality control tests before being shipped:

- Moisture content
- Hardness
- Bulk density
- Ash content
- Sodium thiosulfate content

### Service

AAF International would be pleased to offer you a maintenance contract for your chemical filter system. This includes sampling, removal of the used elements, cleaning of the installation and installation of new elements. Disposal in accordance with regulations and/or refilling is part of our scope.



# SAAFCarb™ MA Plus

## Specification

Physical Properties	
Moisture content	< 15 (wt %) acc. ASTM D2867
BET rating, active area	>1100 (m <sup>2</sup> /g) acc. DIN 66132
Abrasion resistance	> 95 (%) acc. ASTM D3802
Ash content	< 8 (wt %) acc. ASTM D2866
Apparent bulk density	500 (kg/m <sup>3</sup> ) acc. ASTM D2854
Nominal pellet diameter	3 mm
CTC rating	> 65 (wt%) acc. ASTM D3467

## Application guidelines

Packaging Options	
Containers	25 kg sacks
Big Bags	500 kg big bags
Ready factory filled into:	SAAF Canisters, Cassettes, Trays and deep bed filters
Media Selection	Target contaminants
SAAFCarb™ MA Plus	Hydrogen Sulfide (H <sub>2</sub> S) Sulfur dioxide (SO <sub>2</sub> ) Chlorine (Cl <sub>2</sub> ) Hydrocarbons (VOC's)
Performance	
Temperature	-20 °C to 55 °C
Humidity	10 - 95 % r. H.
Applications	
Airflow	From 40 m <sup>3</sup> /h to over 170.000 m <sup>3</sup> /h
Velocity	From 0,30 to 2,5 m/s
Precautions	
Installation	Use dust masks, safety goggles, and rubber gloves
MSDS	Included in each shipment
Safety	Wet activated carbon adsorbs atmospheric oxygen, causing low oxygen supply in enclosed areas or packed containers. This can be potentially hazardous for workers who enter these oxygen depleted areas
Disposal	Must be disposed off according to local, state, and federal regulations

Please refer to appropriate AAF documentation for additional information on delivery systems



AAF International  
European Headquarters  
Robert-Bosch-Straße 30-32, 64625 Bensheim  
Tel: +49 6251 80368 – 0, Fax +49 6251 80368 – 20  
aafintl.com

AAF International has a policy of continuous product research and improvement and reserves the right to change design and specifications without notice.

©2017 AAF International and its affiliated companies.  
GPF\_707\_EN\_042018